

DULUX ODOURLESS INTERIOR STAIN BLOCKING PRIMER 30000

Solvent based product, white

Technical Data Sheet



Technical Specifications (21°C (70°F))

Solids by Volume – 46% (+/- 1%)
Solids by Weight – 75% (+/- 1%)

Volatile Organic Compounds (VOCs)*

According to ASTM D3960-05: < 350g/L
Canadian regulation: < 350 g/L

Colour

White (can be tinted to light pastel colours,
max 2 oz. of colourant per litre)

Gloss Level

• N/A

Practical Coverage

380 - 420 sq. ft. per 3.78 litres
9 - 10 sq. metres per litre
(Actual coverage will vary depending on substrate
and application method.)

Resin Type

• Synthetic Resins

Diluent

• Hydrocarbons

Viscosity* Ready to use (82 - 92 Krebs Units)

Flammability Combustible liquid

Flash Point* 39°C (102°F)

Recommended Film Thickness*

• Wet: 4.0 mils
• Dry: 1.8 mils

Drying Time* @ 77°F/25°C - 50% Relative Humidity

**Drying & recoat times are dependent on temperature,
humidity, ventilation and film thickness*

Touch dry: 30 minutes
To recoat: 2 hours
Before cleaning: 7 – 10 days

Product Description

Dulux Odourless Interior Stain Blocking Primer 30000 is formulated with synthetic resin in a solvent base. Dulux Odourless provides great leveling properties and a fast drying time. Effective for most killing stains especially water stains, fire and smoke damage, tannin, crayon, lip stick, graffiti, ballpoint pen and food stains.

Dulux Odourless Interior Stain Blocking Primer 30000

- Ready for use and easy to apply.
- Dries quickly and has very little odour.
- Exceptional durability.
- Effectively seals and gives the finishing coats a better appearance.

Intended Uses

- New and maintenance work
- Residential and Commercial sites
- Any interior heavily stained surface
- Not formulated to be used on floors
- Not for use with topcoats containing aromatic hydrocarbons or oxygenated solvents
- Must be coated with paint

*Technical Data Source: 30000

GUARANTEE: Akzo Nobel Canada Inc. guarantees performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other guarantee, expressed or implied, statutory or otherwise is given. We shall not be responsible for any indirect, consequential or other damages. Edition of January 2012



Available at Dulux Paints Stores across Canada and Betonel-Dulux Stores in Québec

SURFACE PREPARATION

All surfaces must be clean, dry and free of dirt, chalk, grease, wax, rust and loose or peeling paint before painting.

- Mildew must be removed by washing affected area with a solution of 30% household bleach and 70% water. Rinse well.
- Remove all loose and peeling paint and sand to smooth edges.
- Repair holes and cracks with filler suitable for the surface to be repaired.
- If wood exudes resin, scrape the excess and clean surface with alcohol or paint thinner.
- Sand all surfaces smooth and lightly sand glossy areas. Vacuum sanding residue.
Precaution: Dry sanding, flame cutting and/or welding of dry paint film will give rise to dust and/or hazardous fumes. Wet sanding should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.

Previously Painted Surfaces: spot prime repairs or any bare areas or total surface where necessary.

New concrete, masonry or plaster: must age at least 30 days and be thoroughly dry before painting.

Bare Wood: sand smooth.

Application

Ready-to-use product, do not thin.

Mix thoroughly before use.

Apply using brushes, rollers or spray equipment. Suitable under latex or alkyd topcoats.

Application Conditions

Apply only when air and surface temperatures are above 50°F (10°C)

Tools

- Brush – Natural bristle or synthetic bristle (nylon, polyester)
- Roller – 10–15 mm
- Spray (Airless equipment) – tip size: 0.013 to 0.019 in - Pressure: 2300 – 2700 psi

*Spray recommendations may vary from figures listed depending on equipment manufacturer

SYSTEM RECOMMENDATIONS

Two topcoats are recommended on all surfaces for better durability and appearance.

All recommended surfaces:

- Dulux Odourless Stain Blocking Primer– one coat to total surface. Some aggressive stains may require a second coat of primer to prevent bleed through.

- Appropriate Dulux topcoat

Clean-up

Remove as much of the product as possible and clean tools with mineral spirits immediately after use.

Storage and Transportation

Keep product cool and dry.

Disposal

Consult your municipality about proper disposal procedures in accordance with the laws and respect the environment or give leftover paint to someone who could use it: a neighbor or friend, a recreational service or a non-profit organization. Do not pour leftover product down the drain.

Safety Measures

Read the Material Safety Data Sheet. Avoid contact with eyes. Keep out of reach of children. Use only in well ventilated areas. Keep away from flames or sparks.

FIRST AID TREATMENT: If in contact with eyes, rinse thoroughly with clear water. If swallowed, do not induce vomiting. Call poison centre or physician immediately.

For product information call: 1-(800)-387-3663
www.dulux.ca